

AMENDMENT

**(Amendment under provision of Article 11
corresponding to PCT Article 34)**

To: Kouzou OIKAWA, Director-General of the Patent Office

1. Identification of PCT Application PCT/JP00/03399

2. Applicant

Name: JAPAN SCIENCE AND TECHNOLOGY CORPORATION
Address: 1-8, Hon-cho 4-chome, Kawaguchi-shi,
Saitama 332-0012 JAPAN
Nationality: JAPAN
Residence: JAPAN

3. Agent

Name: (8068) OGAWA Junzo, Patent Attorney
Address: Kobikikan Ginza Bldg, 8-9, Ginza
2-chome, Chuo-ku, Tokyo, 104-0061 Japan
TEL: 03-3561-2211

4. Target of Amendment "Specification" and "Claims"

5. Content of the amendment

A. Explanation of amendment content of Claims

- (1) Please amend "Cr: not less than 60 mass%" to "Cr: exceeding 60 mass%" in claim 1.**
- (2) Please add "A Cr-based alloy having an excellent strength-ductility balance at higher temperature, comprising Cr: not less than 65 mass%, C+N: not more than 20 mass ppm, S: not more than 20 mass ppm, O not more than 100 mass ppm, O as an oxide: not more than 50 mass ppm, and the remainder being Fe and inevitable impurities." as claim 2.**
- (3) Please add "A Cr-based alloy according to claims 1 and 2, having a strength-ductility balance of $RA \times TS \geq 10000$ (%·MPa) at higher than 1000 °C." as claim 3.**
- (4) Please add "A Cr-based alloy described in claims 1 and 2, having strength-ductility balance of $RA \times TS \geq 10000$ (%·MPa) at 1050°C-1200°C." as claim 4.**

B. Explanation of amendment content of Specification

(1) Please amend "JP-A-55-154542" on line 20, in page 1 of Specification to "JP-B-64-7145".

(2) Please amend "Cr: not less than 60 mass%" on line 1, in page 3 to "Cr: exceeding 60 mass%".

(3) Please add "And also, the invention lies in a Cr-based alloy having an excellent strength-ductility balance at higher temperatures, comprising Cr: not less than 65 mass%, C+N: not less than 20 mass ppm, S: not more than 20 mass ppm, O: not more than 100 mass ppm, O as an oxide: not more than 50 mass ppm, and the remainder being Fe and inevitable impurities."

Furthermore, the invention relates to what has a strength-ductility balance of $RA \times TS \geq 10000$ (% · MPa) at higher than 1000°C in each above-mentioned invention. And also, the invention relates to what has $RA \times TS \geq 10000$ (% · MPa) in each above-mentioned invention at 1050°C~1200°C." after "...impurities." on line 4, page 3 of Specification.

6. List of documents attached

- (1) New pages of the specification 1set
(Pages 1, 3 and 3/1, corresponding to the replaced pages 1, 2 and 2/1 of the Japanese text)
- (2) New page of claims 1set
(page 10, corresponding to the replaced page 9 of the Japanese text)